

N10

EN-Standard

Basisglas	Ebene	Glasstärke [mm]	sichtbarer Lichtbereich			solare Strahlung			g-Wert [%]	b-Wert (g-Wert/0,8) [%]	shading coefficient (g-Wert/0,87) [%]	Farbwieder- gabeindex R _a	U _g -Wert [W/m ² K] (90% Argon)
			Trans- mission [%]	Reflexion [%]		Trans- mission [%]	Reflexion [%]	Absorption [%]					
				außen	innen								
substrate	coated glass surface	standard thickness [mm]	visible light			total solar energy			solar factor (SF) [%]	b-value (SF/0.8) [%]	shading coefficient (SF/0.87) [%]	colour rendering index	U _g -value [W/m ² K] (90% argon)
trans- mittance [%]	reflectance [%]		trans- mittance [%]	reflectance [%]	absorbance [%]								
	outside	inside				outside							
Floatglas clear	#3	4 16 4	70	23	24	43	39	18	50	63	57	97	1,0

Glasfarben abweichend von Farben in diesem Prospekt.

Alle technischen Werte nach EN 410 und EN 673 (ΔT = 15 K), Produktionstoleranzen nach EN 1096.

Alle Produkte sind ausschließlich für den Einsatz auf Ebene #3 freigegeben.

Für den Einsatz auf anderen Ebenen bitte den arcon-Vertrieb kontaktieren.

Werte können sich im Zuge der Produktweiterentwicklung ändern. Irrtümer und Fehler nicht ausgeschlossen.

Stand: August 2014 Deh

Glass colours shown are for reference only and do not represent actual glass colour.

Performance data are calculated using EN 410 and EN 673 (ΔT = 15 K), manufacturing tolerances EN 1096.

All products are approved only for use on surface #3.

For use on different surfaces please contact arcon sales personal in advance.

arcon reserves the right to change product performance characteristics without notice and without obligation.

rev: August 2014 Deh